

Peran TCW

Product sheet

Product description

Peran TCW is a thixotropic 2-component, epoxy topcoat, resistant to early contact with water (24 hours @ 20°C). The topcoat produces a hard, impermeable and repellent surface with good resistance to chemicals.

Uses

Peran TCW is used as a thixotropic sealer coat for skirting and coves, and in the Peran Floor and Wall Flake systems.

Environment & Health

Peran TCW is a solvent and nonylphenol free product, and practically odourless during application. Follow the appropriate Occupational Health and Safety guidelines applicable to the location where the application is undertaken.

For more information, please refer to the safety datasheets for the individual components.

Ratio of components

2 parts of component A are mixed with 1 part of component B, by weight.

1.8 parts of component A are mixed with 1 part of component B, by volume.

Add all of Hardener B to Base A. Mix with slow speed drill and helical spinner, taking care not to entrain air.

Application temperature

The recommended substrate temperature is 15-25°C, but no less than 10°C.

The temperature of the substrate should exceed the "dew point" by 3°C during application and hardening.

Application time/pot life

Ready-mixed product should be used within 30 minutes at a temperature of 18°C.

At higher temperatures the application time is shorter.

Curing time (20°C)

Can be overcoated after 15 hours.

Can be walked on after 15 hours.

Maximum overcoat time 24 hours

The product is fully hardened after 5-7 days.

High humidity in the early stages of cure can result in white, matt surfaces (blooming).

Do not cover or wash within the first 16 hours of curing.

Colours

Transparent.

Solids content

Approx. 100 %.

Finish

Gloss.

Density

Component A approx. 1.13 kg/l.

Component B approx. 1.01 kg/l.

A+B approx. 1.09 kg/l.

Storage

12 months in unopened pack at a temperature of 5-40°C.

Protect from weather and moisture/contaminant ingress.

Packaging

The product is delivered A+B in the following packs:-

		Base A	Hardener B
2.4 kg	(2.2 litres)	1.6 kg	0.8 kg
12 kg	(10.9 litres)	8 kg	4 kg
			48 kg
			300 kg
			500 kg

Any recommendation or suggestion relating to the use of the products made by Flowcrete UK Ltd., whether in its technical literature, or in response to a specific enquiry, or otherwise, is based upon data believed to be reliable, however the products and information are intended for use by Customers having requisite skill and know-how in the industry and therefore it is for the Customer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that the Customer has done so at its sole discretion and risk.